



RUST AND CORROSION BARRIER COATING

COLOR SELECTION:

28-60 RED, 28-61 GRAY, 28-62 BLACK, 28-63 YELLOW, 28-67 WHITE, 28-68 BLUE, 28-70 GREEN, 28-71 SAFETY YELLOW, 28-72 SAFETY RED, 28-95 TAN

PRODUCT DESCRIPTION:

ZERO RUST® is a high solids, low VOC phenolic modified alkyd coating which controls rust and corrosion by putting down an impermeable barrier at the steel level. ZERO RUST® is a single package air dry direct to metal coating which contains no lead or isocyanates.

PRODUCT USES:

Perfect for new and old steel, rusty surfaces and partially rusted , partially painted surfaces.

SURFACE PREPARATION:

FOR COMPLETE PROCEDURES REFER TO THE APPLICATION GUIDE

GENERAL- Thoroughly clean all surfaces of any dirt, oil, grease, silicone and any other contaminants. Remove all loose rust. As with any paint product, a direct relationship exists between surface preparation and product performance

METHOD OF APPLICATION:

MIX THOROUGHLY BEFORE USING. Apply with brush, roll or spray. Application with airless spray equipment requires thinning and can be done directly from the can.

DIRECTIONS FOR USE: MIX THOROUGHLY BEFORE USING!

For best results apply a minimum of two coats, using a crisscross pattern from one coat to the next to help preclude pinholes and thin spots. Allow adequate time between coats for flash off, 20-30 minutes is typical. Apply only at recommended spread rate to ensure adhesion and dry.

DRY TIME:

Drying conditions will vary greatly depending on applied film thickness, thinning, air movement, relative humidity and temperature. ZERO RUST® dries to the touch in 30 minutes and is tack free within one hour.

THIINNING AND CLEANUP:

Recommended thinners – Xylene, Lacquer Thinner, Acetone and Oxsol 100.

Cleanup and Disposal – Clean with Methyl Ethyl Ketone (MEK), Xylene or Lacquer Thinner. Dispose of wastes and residue in accordance with regulations applicable to the area of use.

WARNING: ZERO RUST® is not recommended for submersion applications.

PHYSICAL DATA:

Solids by Weight	66-70%
Solids by Volume	52-55%
Weight by Gallon	10.6 ±2
Viscosity	72-80KU
Maximum Coating VOC	420 grams/liter

COVERAGE:

288 square feet per gallon for recommended 3 mils dft

AVAILABLE SIZES:

ZERO RUST® is available in 12oz Aerosols, Quarts, Gallons and 5 gallon pails.

ZR1 Coatings Inc. 2762 Barrett Station Rd. Des Peres MO 63021